

## TECHNICAL DESCRIPTION

# EUROTROD LR 47

### CERTIFIED COMPANY:



APCER  
CERTIFICADO  
N. 2000/CEP. 1272  
SISTEMA PORTUGUÊS  
DA QUALIDADE  
NP EN ISO 9001



### CLASSIFICATION:

**AWS A5.4: ~E 307-16**  
**EN 1600: 18 8 Mn R 12**

### DESCRIPTION:

Rutile type electrode, particularly suitable for difficult weld steels, manganese-alloyed steels, joining dissimilar steels. Suitable as a buffer layer when hard facing and as pure hard facing of parts subject to extreme impact conditions.

### SUITABLE FOR:

Difficult weld steels, e.g. unalloyed and high-strength alloy steels, carbon steels, high-alloy steels, tool steels, heat treating steels, spring steels, rail steels, manganese hardening steels.

### TYPICAL CHARACTERISTICS OF ALL-WELD METAL:

#### Chemical Analysis (%):

C	Si	Mn	Cr	Ni			
0,11	1,10	4,60	19,0	9,0			

#### Mechanical Properties:

Yield Strength (N/mm <sup>2</sup> )	Tensile Strength (N/mm <sup>2</sup> )	Elongation 5d (%)	Hardness HB > 200 Considerable increase in hardness to 450 HB as a result of cold forming
>350	>500	>25	

### PRODUCT INFORMATION:

WELDING PARAMETERS				VACUUM PACKING	
Diameter (mm)	Length (mm)	Recommended Current (A)	Current Type (Pole +)	Pieces /Packet (Un)	Weight /Packet (Kg)
2,5	300	50 – 70	AC/DC	110	1,8
3,2	350	95 – 120	AC/DC	65	2,0
4,0	350	120 – 160	AC/DC	40	2,0
5,0	350	160 – 200	AC/DC	27	2,0

### WELDING POSITIONS:

